

**SPECIFICATIONS**

Refined and airy gray marble tones with a natural split face.

	<b>THIN VENEER</b>
<b>LENGTH</b>	4" - 30" Random
<b>HEIGHT</b>	2" - 9" Random
<b>THICKNESS</b>	¾" - 1 ½"
<b>YIELD</b>	10-15 lbs/ft <sup>2</sup>

**ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY**

<b>WATER ABSORPTION</b>	.10%
<b>BULK SPECIFIC GRAVITY</b>	2.906

**ASTM C-170 – COMPRESSIVE STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	21,493 psi
<b>PARALLEL TO RIFT, WET</b>	21,626 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	19,688 psi
<b>PERPENDICULAR TO RIFT, WET</b>	13,472 psi

**ASTM C-99 – MODULUS OF RUPTURE**

<b>PARALLEL TO RIFT DRY</b>	2,081 psi
<b>PARALLEL TO RIFT, WET</b>	1,855 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	2,189 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,825 psi

**ASTM C-880 – FLEXURAL STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	2,300 psi
<b>PARALLEL TO RIFT, WET</b>	2,110 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	1,249 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,683 psi



(573) 302-8855

