

**SPECIFICATIONS**

A radiant and sparkling burgundy rose quartzite in an elegant castle cut.

**THIN VENEER**

<b>LENGTH</b>	4" - 24" Random
<b>HEIGHT</b>	4" - 12" Random
<b>THICKNESS</b>	3/4" - 1 1/2"
<b>YIELD</b>	10-15 lbs/ft <sup>2</sup>

**ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY**

<b>WATER ABSORPTION</b>	.12%
<b>BULK SPECIFIC GRAVITY</b>	2.65

**ASTM C-170 – COMPRESSIVE STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	26,530 psi
<b>PARALLEL TO RIFT, WET</b>	26,460 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	20,450 psi
<b>PERPENDICULAR TO RIFT, WET</b>	11,600 psi

**ASTM C-99 – MODULUS OF RUPTURE**

<b>PARALLEL TO RIFT DRY</b>	2,020 psi
<b>PARALLEL TO RIFT, WET</b>	1,550 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	2,140 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,700 psi

**ASTM C-880 – FLEXURAL STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	2,390 psi
<b>PARALLEL TO RIFT, WET</b>	2,270 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	2,450 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,950 psi



(573) 302-8855

