

**SPECIFICATIONS**

A taupe-gray granite with unique graining and lustrous schist character.

**THIN VENEER**

<b>LENGTH</b>	4" - 30" Random
<b>HEIGHT*</b>	Sawn 2 1/4", 5", & 7 3/4"
<b>THICKNESS</b>	3/4" - 1 1/2"
<b>YIELD</b>	10-15 lbs/ft <sup>2</sup>

\*Typical height ratio: 20% = 2 1/4", 50% = 5", 30% = 7 3/4". Additional heights available upon request

**ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY**

<b>WATER ABSORPTION</b>	.16%
<b>BULK SPECIFIC GRAVITY</b>	2.691

**ASTM C-170 – COMPRESSIVE STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	31,250 psi
<b>PARALLEL TO RIFT, WET</b>	17,640 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	27,190 psi
<b>PERPENDICULAR TO RIFT, WET</b>	19,710 psi

**ASTM C-99 – MODULUS OF RUPTURE**

<b>PARALLEL TO RIFT DRY</b>	1,860 psi
<b>PARALLEL TO RIFT, WET</b>	1,050 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	2,910 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,680 psi

**ASTM C-880 – FLEXURAL STRENGTH**

<b>PARALLEL TO RIFT DRY</b>	3,960 psi
<b>PARALLEL TO RIFT, WET</b>	2,080 psi
<b>PERPENDICULAR TO RIFT, DRY</b>	3,030 psi
<b>PERPENDICULAR TO RIFT, WET</b>	1,770 psi



(573) 302-8855

